



Wellamid®
ENGINEERING RESIN

Guide to Molding

Wellamid® GF14-60 XE-NBK1

Glass Fiber Reinforced Nylon Resin (PA6)

Screw Machine	°F	°C
Rear Zone	500 - 550	260 - 288
Middle Zone	490 - 550	254 - 288
Front Zone	480 - 550	249 - 288
Nozzle Temp	470 - 550	243 - 288
Melt Temp	500 - 550	260 - 288
Mold Temp	160 - 200	71 - 93
Injection Pressure	5,000 - 20,000 PSI	34 - 138 MPa
Back Pressure	50 - 150 PSI	0.34 - 1.03 MPa
Screw RPM	30 - 120 RPM	30 - 120 RPM

DRYING

Wellamid® nylon resins shipped in bags are ready to mold with moisture content below 0.15%.

Nylon resins are hygroscopic and must be molded at a moisture level between .05% - .15% for best results. All **Wellamid®** nylon resins residing in opened bags or Gaylord boxes should be dried for 2 to 4 hours at 175°F prior to molding. It is highly recommended to check the moisture content of the material before and during the molding process. Maintaining a moisture level between .05% - .15% helps prevent degradation which manifests itself by splay marks, low physical properties, brittleness, and nozzle drool.

PROCESSING

Although not required, Wellman Engineering Resins highly recommends running a reverse heat profile on all **Wellamid®** nylon resins. This method produces a more homogenous melt and also assists in the control of nozzle drool. Reverse-taper nozzle tips are always recommended with the use of **Wellamid®** nylon resins also.

For further technical information please go to www.wellmanam.com or call 1 800 821-6022.